

# BRYAN ROCK PRODUCTS, INC.

Box 215 • Shakopee, MN 55379  
Phone (952) 445-3900 • (800) 382-3756 • Fax (952) 445-0809  
www.bryanrock.com

## SPECIFICATIONS

For  
Red Ball Diamond Aggregate  
(RBDA)

### (A)

100% Crushed Red Dolomitic Limestone from  
the Oneota Dolomite member of the  
Prairie du Chien Limestone deposit group.

### (B)

The Color must be red as compared to  
Bryan Rock Products at Shakopee, MN quarry.

### (C)

#### Gradation Requirements

##### % Passing Screens

3/8"	100%
# 4	95-100%
# 40	35-50%
# 80	25-35
#200	15-25%

### (D)

(% ASTM: C127)	Absorption	Not Greater than	4.0
(ASTM: C131)	Abrasion Loss (LAR)	Not Greater than	40
(ASTM: C88)	Soundness Loss (5 Cycle MG-So4)	Max Allowed	15
(ASTM: D4318)	Atterberg Limits:		
	Liquid Limits	Max Allowed	25
	Plasticity Index	Max Allowed	6
(ASTM: D3042)	% Insoluble Residue Passing #200 Sieve	Not Greater than	10